



## CZHK

### Heavy Weight, Knife Cut, Laundered, Stacked

Technical Data			
Particle Generation	Average	100% continuous filament, textured, high bulk polyester	
<b>Biaxial Shake, particles Total &gt;0.5<math>\mu</math>m (X10<sup>6</sup>)</b>	<b>5.042</b>	<b>Weight</b>	<b>4.1 Ounces per square yard +/- .2 Oz.</b>
<b>Biaxial Shake, fibers Total (<math>\geq</math>100<math>\mu</math>m)/m<sup>2</sup></b>	<b>.2439</b>	<b>Size</b>	<b>9" x 9"</b>
<b>Total Extractables</b>		<b>Color</b>	<b>White</b>
<b>Deionized Water g/m<sup>2</sup></b>	<b>.0138</b>	<b>Edges</b>	<b>Knife Cut</b>
<b>Isopropyl Alcohol g/m<sup>2</sup></b>	<b>.0451</b>	<b>Laundered</b>	<b>Class 4 or Higher Cleanroom Laundry</b>
<b>Ions</b>		<b>Packed</b>	<b>Stacked</b>
<b>Sodium ppm</b>	<b>.1822</b>	<b>Seal</b>	<b>Vacuum Sealed</b>
<b>Chloride ppm</b>	<b>.0466</b>	<b>Quantity Per Pack</b>	<b>Depends upon wipe size and customer needs</b>
<b>Potassium ppm</b>	<b>.1551</b>	<b>Units Per Case</b>	<b>Depends upon wipe size and customer needs</b>
<b>Absorbency</b>		<b>Packaging</b>	<b>Double Bagged with Case Liner</b>
<b>Absorbent Capacity (mL/m<sup>2</sup>)</b>	<b>290</b>		
<b>Absorbency Rate seconds</b>	<b>1</b>		